

TITAN LAM 300 GLOSS | TLG-300

Heavy-duty high gloss overlam developed for long term applications on powervehicles.

FACE FILM

Polymeric PVC, gloss clear

Thickness (µm)	300	
Tensile strength (N/cm)	75	DIN EN ISO 527
Elongation at break (%)	>100	DIN EN ISO 527

ADHESIVE

Clear solvent-based acrylic, permanent

Thickness (µm)	30	
Adhesion to steel		FINAT FTM 1
20 minutes (180°) N/25mm	25	
24 hours (180°) N/25mm	31	

RELEASE LINER

Clear PET liner

Thickness (µm)	75	
----------------	----	--

PRODUCT APPLICATION

Application method	Cold lamination (<30°C)	
Application temperature (°C)	10 to 30	
Service temperature (°C)	-20 to 70	

DURABILITY

Shelf life (months)	12	
Outdoor durability (years)	6	Northern-EU climate, vertical exposure

ROLL SIZES

1370mm x 25m

Fourbases BV guarantees the material for twelve months from the date of final invoice. The shelf life of our material depends on storage conditions. The end user should store the material in the original boxes or in equivalent boxes, away from direct sunlight, at a temperature of 21°C and 50% relative humidity. Fourbases BV guarantees that the products are free from defects in workmanship or defects in TITAN material, provided they are stored properly. At its sole discretion, Fourbases BV may either: (1) replace all or part of the materials, or (2) issue a credit note for the value of the defective portion. All quoted data values are typical and should not be used as a basis to consider the product defective if measured values differ.